C PLASTICS INTERNATIONAL SHEET, ROD, TUBE, FILM...CUT TO SIZE

Teflon® PTFE (Polytetrafluoroethylene)

PTFE resin is in a class of paraffinic polymers that have some or all of the hydrogen replaced by fluoride. The original PTFE resin was invented by DuPont in 1938 and called Teflon[®].

PTFE is a crystalline polymer with a melting point of about 621° F (327° C). Density is 2.13 to 2.19 gm/cc. PTFE has exceptional resistance to chemicals. Its dielectric constant (2.1) and loss factor are low and stable across wide temperature and frequency range.

PTFE has useful mechanical properties from cryogenic temperatures at 500° F (280° C) continuous service temperatures. Its coefficient of friction is lower than almost any other material. It also has a high oxygen level.

| Property | ASTM Test Method | Units | Teflon® PTFE |
|-------------------------------------|------------------------|--------------|------------------|
| Physical | | | |
| Specific Gravity | D792 | | 2.13-2.22 |
| Mechanical | | | |
| Tensile Strength | D1457 D1708 D638 | psi | 3,000-5,000 |
| Elongation | D1457 D1708 D638 | % | 300-500 |
| Flexural Modulus | D790 | psi | 72,000 |
| Folding Endurance | D2176 | (MIT) cycles | >10 ⁶ |
| Impact Strength | D256 | ft-lb/in | 3.5 |
| Hardness, Shore D | D2240 | | 50-65 |
| Coefficient of Friction, Dynamic | D1894 | <10 ft/min | 0.1 |
| Thermal | | | |
| Melting Point | D3418 | °F | 621 |
| Upper Service Temperature (20,000h) | UL746B | °F | 500 |
| Flame Rating | UL94 | | V-0 |
| Limiting Oxygen Index | D2863 | % | >95 |
| Heat of Combustion | D240 | Btu/Ib | 2,200 |

NOTE: The information contained herein are typical values intended for reference and comparison purposes only. They should NOT be used as a basis for design specifications or quality control. Contact us for manufacturers' complete material property datasheets. All values at 73°F (23°C) unless otherwise noted.