

Delrin® Changes Reference Sheet

DuPont has been consolidating their resin offerings. The following is a summary of data comparing the properties of the obsolete grades to the “new” grades.

Delrin® 550SA NC010 was discontinued at the end of 2002. Delrin® 511P NC010 is the replacement grade.

Delrin® II 150SA NC010 and Delrin® II 150E NC010 were discontinued at the end of 2003. Delrin® 150 NC010 is the replacement grade.

Property	Units	NEW	DISCONTINUED	NEW	DISCONTINUED	DISCONTINUED
		Delrin® 511P NC010	Delrin II® 550SA NC010	Delrin® 150 NC010	Delrin® II150SA NC010	Delrin® II150E NC010
Tensile Strength @ Yield	psi	10,400	10,000	10,400	10,000	10,000
Elongation @ break	%	33	40	40	84	80
Tensile Modulus	psi	490,000	450,000	450,000	400,000	400,000
Flexural Strength	psi	15,000	14,100		14,300	14,300
Flexural Modulus	psi	480,000	430,000	440,000	420,000	420,000
Notched Izod Impact Strength	ft-lb/in	1.4	1.5	n/a	2.4	2.4
Heat Deflection Temperature @ 66 psi	°F	336	334	327	336	336
Heat Deflection Temperature @ 264 psi	°F	237	264	212	257	257
Melting Point	°F	352	347	352	352	352
Coefficient of Linear Thermal Expansion (73 – 130 °F)	10 ⁻⁵ in/in/°F	6.2			6.7	6.7
Specific Gravity		1.42	1.42	1.42	1.42	1.42
Water Absorption 24 hr Immersion	%	0.3	0.25	0.25	0.25	0.25
Flammability	UL-94	HB (0.75mm)	HB (0.75mm)	HB (0.75mm)	HB (0.75mm)	HB (0.75mm)

Regulatory Summary					
	Delrin® 511P NC010	Delrin II® 550SA NC010	Delrin® 150 NC010	Delrin® II150SA NC010	Delrin® II150E NC010
FDA 21 CFR177.2480 for repeated food contact up to 212 °F except those containing 8% alcohol	yes	yes	yes	yes	yes
NSF Standard 61	yes	yes	yes	yes	yes
ASTM D 4181	POM 112	POM110 B44350	POM111	POM 110 B34330 and 4181-94b POM111	POM111
ASTM D 6100	S-POM0112	S-POM0112	S- POM0111	S-POM0111	S- POM0111
USP Class VI	no	no	no	no	no

We believe this information is the best currently available on the subject. It is subject to revision as additional knowledge and experience is gained. Plastics International makes no guarantee of results and assumes no obligation of liability whatsoever in connection with this information. Anyone intending to use recommendations contained in this publication should first satisfy himself that the recommendations are suitable for his use and meet all appropriate safety and health standards. This publication is not a license to operate under, or intended to suggest infringement of any existing patents.